




# Power Goals for NASA's Exploration Program

J. Jeevarajan, Ph.D.  
COTR / Senior Scientist  
NASA-JSC, Houston, TX



# Exploration Program



# NASA's Exploration Roadmap



05 06 07 08 09 10 11 12 13 14 15 16 17 18 19 20 21 22 23 24 25...




Exploration and Science Lunar Robotics Missions



Lunar Outpost Buildup

Research and Technology Development on ISS

Commercial Orbital Transportation Services for ISS



Space Shuttle Operations

SSP Transition

Ares I and Orion Development

Operations Capability Development  
(EVA Systems, Ground Operations, Mission Operations)



Ares I-X  
Test Flight  
April 2009

Orion and Ares I Production and Operation

Altair Development



Ares V & Earth Departure Stage

Surface Systems Development



# Our Exploration Fleet

## *What Will the Vehicles Look Like?*



Earth Departure Stage




Ares V  
Cargo Launch  
Vehicle



Orion  
Crew Exploration  
Vehicle



Altair  
Lunar  
Lander




Ares I  
Crew Launch  
Vehicle



# Building on a Foundation of Proven Technologies

## - Launch Vehicle Comparisons -




DAC 2 TR 6  
LV 51.00.48

# Ares 1-X



J. Jeevarajan, Ph.D. / NASA-JSC

# Ares 1-X







# Ares I



# Orion CEV and ISS





# Ares V





Composite Payload Shroud



Altair Lunar Lander



Earth Departure Stage  
 LOx/LH<sub>2</sub>  
 1 J-2X Engine  
 Al-Li Tanks  
 Composite Structures



Loiter Skirt



Composite Interstage




Core Stage  
 LOx/LH<sub>2</sub>  
 6 RS-68B Engines  
 Al-Li Tanks  
 Composite Structures

2 5.5-Segment RSRBs

# Ares V




# Altair Lunar Lander



# Lunar Mobility



# Lunar Outpost



# Lunar Surface Systems (Mobility)

## Pressurized Rover



Preliminary Power Requirements:  
**Safe**, reliable operation  
>150 Wh/kg at battery level  
> 100 cycles  
Operation Temp: 0 to 30 °C  
Maintenance-free operation




# Altair Lunar Lander Ascent Module

**Preliminary Power Requirements for Minimum capability (no redundancy):**

- **Safe, reliable operation**
- **14 kWh energy, delivered**
- **1.67 kW average and 2 kW peak power**
- **Mass allocation: 67 kg**
- **Volume allocation: 45 liters**
- **7 hours continuous operation**
- **1 cycle**
- **Operation over 0 – 30 degrees C**
- **Operation in 0 – 1/6 G**

## **Ascent Stage: Batteries**

(Current baseline is Primary Lithium Battery with plan to change to rechargeable Li-ion)  
Required to provide contingency power for descent stage and translunar insertion; expect peak power growth; Rechargeable provides greater ability to test before flight.



# Extravehicular Activity (EVA) Suit

## Lunar EVA 2<sup>nd</sup> Configuration


### Enhanced Helmet Hardware:

- Lighting
- Heads-Up-Display
- Soft Upper Torso (SUT) Integrated Audio

### Power / Communications, Avionics & Informatics (CAI):

- Cmd/Cntrl/Comm Info (C3I)
- Processing
- Expanded set of suit sensors
- Advanced Caution & Warning
- Displays and Productivity Enhancements

Video:  
Suit Camera



### PLSS:

Fan, pump, ventilation subsystem processor; Heater, controllers, and valve

### Enhanced Liquid Cooling Garment:

- Bio-Med Sensors

### Preliminary Power Requirements:

- Safe, reliable operation
- 1155 Whr energy, delivered
- 145 W average and 233 W peak power
- Mass allocation: 5 kg
- Volume allocation: 1.6 liters
- 8 hour operation per sortie
- 100 cycles (operation every other day for 6 mos.)
- Operation over 0 – 30 degrees C

### Current Suit Batteries:


EMU: 20.5 V; min 26.6 Ah (7 hr EVA), 9A peak, 5 yr, <15.5 lbs, 30 cycles

SAFER: 42 V; 4.2 Ah (in emergency only)

REBA: 12.5 V, 15 Ah, (7 hr EVA); 5 yr, ~6 lbs

EHIP: 6 V, 10.8 Ah; (7 hr EVA); 5 yr, ~1.8 lbs

# Energy Storage Battery Development Schedule for Constellation





# Key Performance Parameters for Battery Technology Development

Customer Need	Performance Parameter	State-of-the-Art	Current Value	Threshold Value	Goal
<b>Safe, reliable operation</b>	No fire or flame	Instrumentation/controllers used to prevent unsafe conditions. There is no non-flammable electrolyte in SOA	Preliminary results indicate a moderate reduction in the performance with flame retardants and non-flammable electrolytes	Benign cell venting without fire or flame and reduce the likelihood and severity of a fire in the event of a thermal runaway	Tolerant to electrical and thermal abuse such as over-temperature, over-charge, reversal, and external short circuit with no fire or flame
<b>Specific energy</b> <u>Lander:</u> 150 – 210 Wh/kg 10 cycles  <u>Rover:</u> 150 – 200 Wh/kg  <u>EVA:</u> 200 – 300 Wh/kg 100 cycles	<b>Battery-level</b> specific energy*	90 Wh/kg at C/10 & 30 C 83 Wh/kg at C/10 & 0 C (MER rovers)	130 Wh/kg at C/10 & 30 C 120 Wh/kg at C/10 & 0 C	<b>135 Wh/kg</b> at C/10 & 0 C “High-Energy”** <b>150 Wh/kg</b> at C/10 & 0 C “Ultra-High Energy”**	<b>150 Wh/kg</b> at C/10 & 0 C “High-Energy” <b>220 Wh/kg</b> at C/10 & 0 C “Ultra-High Energy”
	<b>Cell-level</b> specific energy	130 Wh/kg at C/10 & 30 C 118 Wh/kg at C/10 & 0 C	150 Wh/kg at C/10 & 0°C	<b>165 Wh/kg</b> at C/10 & 0 C “High-Energy” <b>180 Wh/kg</b> at C/10 & 0 C “Ultra-High Energy”	<b>180 Wh/kg</b> at C/10 & 0 C “High-Energy” <b>260 Wh/kg</b> at C/10 & 0 C “Ultra-High Energy”
	<b>Cathode-level</b> specific capacity Li(Li,NiMn)O <sub>2</sub>	140 – 150 mAh/g typical	Li(Li <sub>0.17</sub> Ni <sub>0.25</sub> Mn <sub>0.58</sub> )O <sub>2</sub> : 240 mAh/g at C/10 & 25°C Li(Li <sub>0.2</sub> Ni <sub>0.13</sub> Mn <sub>0.54</sub> Co <sub>0.13</sub> )O <sub>2</sub> : 250 mAh/g at C/10 & 25°C 200 mAh/g at C/10 & 0°C	<b>260 mAh/g</b> at C/10 & 0 C	<b>280 mAh/g</b> at C/10 & 0 C
	<b>Anode-level</b> specific capacity	320 mAh/g (MCMB)	320 mAh/g MCMB 450 mAh/g Si composite	<b>600 mAh/g</b> at C/10 & 0 C with Si composite	<b>1000 mAh/g</b> at C/10 0 C with Si composite
<b>Energy density</b> Lander: 311 Wh/l Rover: TBD EVA: 240 – 400 Wh/l	<b>Battery-level</b> energy density	250 Wh/l	n/a	<b>270 Wh/l</b> “High-Energy” <b>360 Wh/l</b> “Ultra-High”	<b>320 Wh/l</b> “High-Energy” <b>420 Wh/l</b> “Ultra-High”
	<b>Cell-level</b> energy density	320 Wh/l	n/a	<b>385 Wh/l</b> “High-Energy” <b>460 Wh/l</b> “Ultra-High”	<b>390 Wh/l</b> “High-Energy” <b>530 Wh/l</b> “Ultra-High”
<b>Operating environment</b> 0°C to 30°C, Vacuum	Operating temperature	-20°C to +40°C	-50°C to +40°C	<b>0°C to 30°C</b>	<b>0°C to 30°C</b>


Assumes prismatic cell packaging for threshold values. Goal values include lightweight battery packaging.

\* Battery values are assumed at 100% DOD, discharged at C/10 to 3.0 volts/cell, and at 0°C operating conditions

\*\* “High-Energy” = Exploration Technology Development Program cathode with MCMB graphite anode

“Ultra-High Energy” = Exploration Technology Development Program cathode with Silicon composite anode

# Advanced Lithium-Based Chemistry Cell Development Master Schedule



# EDTP Program Overview

- Two parallel cell development approaches to meet Constellation customer requirements
- High Energy Cell Development
  - **Safe**, reliable Li-ion cell with improved specific energy and energy density over SOA and good cycle life
  - Combination of newly developed cathode, electrolyte, and separator with a carbonaceous anode with known heritage and performance
- Ultra High Energy Cell Development
  - **Safe**, reliable Li-ion system with greatly improved specific energy and energy density over SOA and low cycle life
  - Very high energy system for applications where mass and volume reduction is enabling and cycle requirements are benign
  - Combination of newly developed anode cathode, electrolyte, and separator
  - Higher developmental risk than High Energy Cell
    - Much higher gains in component level specific capacity over conventional electrode materials required for success
    - Addition of a developmental anode increases risk in areas of electrochemical performance, sufficient maturity by need dates, and scalability and manufacturability.
    - Lithium-alloy anode and higher energy chemistry are inherently less safe – component-level inherent safety features more critical

# ETDP Li-ion Cell Development

- **Component-level goals** are being addressed through a combination of NASA in-house materials development efforts, NASA Research Announcement contracts (NRA), and grants
- Materials developed will be delivered to NASA and screened for their electrochemical and thermal performance, and compatibility with other candidate cell components
- Other activities funded through NASA can be leveraged – NASA Small Business Innovative Research (SBIR) Program and Innovative Partnership Program (IPP)
- Leveraging of other government programs (DOD, DOE) for component-level technology

# **Safety Component Development Led by NASA JSC (Judy Jeevarajan)**

- **Development of internal cell materials (active or inactive) designed to improve the inherent safety of the cell**
- **Functional components designed to shut down cell in case of overcharge, over- current, or over-temperature**

# Current State for Safety of Li-ion Batteries

Although the chemistry is one that can provide very high energy density at this time, it is not the safest

- NASA human-rated safety requirement is two-fault tolerance to catastrophic failures – leakage of electrolyte (toxicity hazard), fire, thermal runaway

Hazards encountered during

- Overcharge/overvoltage
- External shorts
- Repeated overdischarge with subsequent overvoltage
- High thermal environments
- Internal Shorts


# Overcharge of Battery Module




**Charge: C/5  
To 4.4 V/Cell  
Overcharge limit:  
5.5 V/Cell  
Thermal runaway  
after 4.8 V/Cell  
Highest temp  
Observed before  
thermal  
runaway: 248 °C**

**41S 5P**


# Overcharge of Li-ion Cell Module



# Current Separators in COTS Cells




Unactivated Separator





Activated Separator

Shut-down temperature is very close to temperature at which initiation of thermal runaway occurs.

# Variable Temperature Shut-down Separators (SBIR)



# SafeLyte<sup>®</sup> Additive (IPP)



# **Composite Thermal Switch (SBIR)**

**Now: 2009 ETDP NRA (NASA Research Announcement)**

**Giner Inc.**

**Development and demonstration of a composite thermal switch for lithium-ion and lithium primary batteries to increase the safety of these batteries by an increase in resistance at high temperatures.**

## **Coating for Improved Cathode Safety (2009 ETDP NRA)**

**Physical Sciences Inc.**

# Screening for Internal Shorts

- NASA –JSC uses vibration method for screening against cell internal shorts.
- Other methods used that can provide screening for internal shorts are X-rays and CT scans.

# Summary

- Safety is top priority for human-rated missions
- Two-fault tolerance to catastrophic failures is required for human-rated safety
- Inherent cell safety can lessen complexity of external protective electronics and prevents dependency on hardware that may also have limitations.
- Inherent cell safety can also remove the need to carry out screening of all cells (X-rays, vibration, etc.)
- For long term missions as in Lunar and Mars programs, safe, high energy/ultra high energy batteries are required.